ENCOR® DL 215

Modified Styrene Butadiene Latex for Specialty Primer Sealer Coatings

and adhesion to galvanized metals. ENCOR® DL 215 latex transition temperature compared to ENCOR® DL 313 latex	has a higher glass
ENCOR® DL 215 latex can also be formulated into sanding	g sealers.
 Modified Styrene Butadiene 	
 Harder version of ENCOR® DL 313 latex Excellent moisture vapor barrier performance Excellent alkali resistance Excellent early adhesion to galvanized metals Improved block resistance and sandability compared to of Good tannin block with tannin blocking pigments 	f ENCOR® DL 313 latex
Total Solids, % by weight	49.0
Weight per Gallon, lb	8.6
pH Value	7.8
Particle Size, microns	0.10
Viscosity, Brookfield, cP	200
Minimum Filming Temperature, °C	NA
Glass Transition Temperature, °C	39
	transition temperature compared to ENCOR® DL 313 latex ENCOR® DL 215 latex can also be formulated into sanding • Modified Styrene Butadiene • Harder version of ENCOR® DL 313 latex • Excellent moisture vapor barrier performance • Excellent alkali resistance • Excellent early adhesion to galvanized metals • Improved block resistance and sandability compared to of • Good tannin block with tannin blocking pigments Total Solids, % by weight Weight per Gallon, lb pH Value Particle Size, microns Viscosity, Brookfield, cP Minimum Filming Temperature, °C

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications.





ENCOR® DL 215

Modified Styrene Butadiene Latex for Specialty Primer Sealer Coatings

Product Safety

Before handling the materials listed in this bulletin, read and understand the product MSDS (Material Safety Data Sheet) for additional information on personal protective equipment and for safety, health and environmental information. For environmental, safety and toxicological information, contact our Customer Service Department at 1-866-837-5532 to find an MSDS, or visit our web site: www.arkemacoatingresins.com

No chemical should be used as or in a food, drug, medical device, or cosmetic, or in a product or process in which it may contact a food, drug, medical device, or cosmetic until the user has determined the suitability and legality of the use. Since government regulations and use conditions are subject to change, it is the user's responsibility to determine that this information is appropriate and suitable under current, applicable laws and regulations.

Arkema Coating Resins requests that the customer read, understand, and comply with the information contained in this publication and the current MSDS(s). The customer should furnish the information in this publication to its employees, contractors, and customers, or any other users of the product(s), and request that they do the same.

Storage and Handling

Follow procedures typically recommended for polymer dispersions. Use corrosion-resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze; store between 4-40°C.



Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511

Telephone: 1.800.777.8227

Visit our website: www.arkemacoatingresins.com

IMPORTANT: The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

© 2012 Arkema Inc. All rights reserved. 10/12 ENCOR® is a registered trademark of Arkema Inc.



ood Chemistry at Work is a registered trademark of the American Chemistry Council Inc.

Page 2 of 2 Form No 309-00266