## SYNOCRYL<sup>®</sup> 874 X 40

**PROTECTIVE & MARINE COATINGS** 

Product Application details	SYNOCRYL <sup>®</sup> 874 X 40 is a thermoplastic acrylic copolymer possessing the gloss retention and exterior durability properties typical of this class of resin. The acrylic monomers used in the manufacture of SYNOCRYL <sup>®</sup> 874 X 40 provide hard and tough films, yet with sufficient plasticising character to main The versatility of SYNOCRYL <sup>®</sup> 874 X 40 enables it to be used in a variety of the sole vehicle in clear or pigmented coatings for metal, wood, plastic a modifying resin to improve the drying time, durability and resistance properties systems. Water white films are deposited from the resin, and clear or pigmented film dry times and are resistant to soaps and detergents. The films are also resist when exposed to heat or ageing. They are far superior to chlorinated rubber terms of colour retention.	were selected to tain flexibility. finishes, either as nd fabrics or as a es of other coating ns possess fast air ant to degradation
Performance Benefits	<ul> <li>Excellent colour retention at elevated temperatures</li> <li>Excellent soap and detergent resistance</li> <li>Good compatibility with a broad range of resins and plasticizers</li> </ul>	
Polymer Type	Solventborne Acrylic	
	Solid Content at 125°C, % (ISO 3251)	39 - 41
Sales Specifications	Viscosity at 25°C, mPa.s (Brookfield RVT , 20rpm, sp3) (ISO 3219)	520 - 750
	Colour, Hazen scale (ISO 6271)	100 max
	Acid value, mg KOH/g (ISO 2114)	10 max
Other Characteristics <sup>1</sup>	Volatile	Xylene
	Flash point, °C (ISO 3679)	26
	Density / Specific Gravity at 20°C, g/ml (ISO 2811)	0.95
	Note: Acid value and/or Hydroxyl value quoted relative to solid resin	
	1 The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications	
Formulation Guidelines	SOLUBILITY SYNOCRYL <sup>®</sup> 874 X 40 is supplied in xylene and is soluble in a range of aromatic hydrocarbons, esters and ketones. The resin has a limited solubility in aliphatic hydrocarbons and alcohols. <u>COMPATIBILITY</u> SYNOCRYL <sup>®</sup> 874 X 40 is compatible with a range of cellulose esters, vinyl resins, chlorinated rubber and acrylated alkyds.	



Product Safety	Please refer to the corresponding Safety Data Sheet.
Storage &	SYNOCRYL <sup>®</sup> 874 X 40 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.
Handling	In the above mentioned storage conditions the shelf life of the resin will be 12 months from the shipping date

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, ARKEMA expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.

See SDS for Health & Safety Considerations.

The products described in the document are not Medical grades designated for Medical Device applications.

Arkema has implemented an internal Medical Policy regarding the use of Arkema products in Medical Devices applications. Arkema has designated Medical grades to be used for Medical Device applications. Products that have not been designated as Medical grades are not authorized by Arkema for use in Medical Device applications. In addition, except for limited cases as determined by the Medical Device Policy, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days. For any use of Arkema's product in Medical Device applications, please contact Arkema's sales network.

Arkema Coating Resins 420, rue d'Estienne d'Orves 92705 Colombes Cedex - France arkema.com - arkemacoatingresins.com

