

SYNOCURE® 854 BA 80

PROTECTIVE & MARINE COATINGS

ARKEMA COATING RESINS

Product Application details SYNOCURE® 854 BA 80 is a high solids hydroxy functional acrylic resin designed for curing at room temperature with suitable polyisocyanates. Suggested applications are protective, marine and maintenance coatings.

Performance Benefits

- Low isocyanate demand
- Economical high solids coatings
- Compliant, low VOC coatings
- Very good gloss retention
- Good all-round performance

Polymer Type

- Solventborne Acrylic

Sales Specifications

| | |
|--------------------------------------|-------------|
| Solid Content at 125°C, % (ISO 3251) | 78 – 82 |
| Viscosity at 25°C, mPa.s (ISO 3219) | 6000 – 9000 |
| Colour, Hazen scale (ISO 6271) | 100 max |
| Acid value, mg KOH/g (ISO 2114) | 10 max |

Other Characteristics¹

| | |
|---|---------------|
| Volatile | Butyl acetate |
| Flash point, °C (ISO 3679) | 24 |
| Density / Specific Gravity at 20°C, g/ml (ISO 2811) | 1.04 |
| Hydroxyl Content, % | 2.1 |
| Hydroxyl Equivalent weight | 810 |

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

SYNOCURE® 854 BA 80 should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The high solids / low viscosity character of SYNOCURE® 854 BA 80 allows low VOC coatings to be formulated even with conventional polyisocyanates. Depending upon formulation <420g/l at 23 seconds cup 4 and <350g/l at 45 seconds cup 4 are possible.

Slightly lower VOC's can be achieved if a lower viscosity isocyanate trimer such as Tolonate® HDT-LV (2) is used.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

$$\text{Hydroxyl equivalent weight} = \frac{17 \times 100}{\% \text{ OH}}$$

$$\text{Isocyanate equivalent weight} = \frac{42 \times 100}{\% \text{ NCO}}$$

Using Desmodur® N 75 series (1), Tolonate™ HDB 75 MX or Tolonate® HDT-LV2 (2), the recommended ratios would be:

Formulation Guidelines

SYNOCURE®

| | On solid resin | As supplied |
|---|----------------|-------------|
| SYNOCURE® 854 BA 80 | 810 | 1013 |
| Desmodur® N 75 series (1) or Tolonate® HDB 75 MX (2) | 191 | 255 |
| Tolonate™ HDT-LV2 (2) | 183 | 183 |

If necessary the initial rate of cure of SYNOCURE® 854 BA 80 based systems can be accelerated by the use of tin catalyst in the form of dibutyl tin dilaurate. Although the level can be varied to suit specific requirements 0.02% of DBTDL based on total solid resin is a good starting point.

SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 854 BA 80 should be free of water and should not contain groups that react with isocyanates. Esters and ketones are true solvents for this type of system and are recommended for use in conjunction with aromatic hydrocarbon diluents such as xylene.

Notes: (1) Bayer MaterialScience, (2) Vencorex Chemicals

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOCURE® 854 BA 80 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months from the shipping date

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Arkema has implemented a Medical Policy regarding the use of Arkema products in medical devices applications that are in contact with the body or circulating bodily fluids (<http://www.arkema.com/en/social-responsibility/responsible-product-management/medical-device-policy/index.html>) Arkema has designated medical grades to be used for such medical device applications. Products that have not been designated as medical grades are not authorized by Arkema for use in medical device applications that are in contact with the body or circulating bodily fluids. In addition, Arkema strictly prohibits the use of any Arkema products in medical device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days. The Arkema trademarks and the Arkema name shall not be used in conjunction with customers' medical devices, including without limitation, permanent or temporary implantable devices, and customers shall not represent to anyone else, that Arkema allows, endorses or permits the use of Arkema products in such medical devices.

It is the sole responsibility of the manufacturer of the medical device to determine the suitability (including biocompatibility) of all raw materials, products and components, including any medical grade Arkema products, in order to ensure that the final end-use product is safe for its end use; performs or functions as intended; and complies with all applicable legal and regulatory requirements (FDA or other national drug agencies). It is the sole responsibility of the manufacturer of the medical device to conduct all necessary tests and inspections and to evaluate the medical device under actual end-use requirements and to adequately advise and warn purchasers, users, and/or learned intermediaries (such as physicians) of pertinent risks and fulfill any postmarket surveillance obligations. Any decision regarding the appropriateness of a particular Arkema material in a particular medical device should be based on the judgment of the manufacturer, seller, the competent authority, and the treating physician.

Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - arkemacoatingresins.com