

# SYNOCURE® 861 X 55

GENERAL INDUSTRY

ARKEMA COATING RESINS

## Product

SYNOCURE® 861 X 55 is a hydroxy functional acrylated polyester designed for crosslinking at both room temperature and low stoving temperatures with suitable polyisocyanates.

## Application details

SYNOCURE® 861 X 55 is primarily intended for use in vehicle refinishing applications, both as a medium for excellent primer surfacers and for finishing coats.

## Performance Benefits

- High solids at application viscosity
- Excellent gloss
- Good sanding properties
- Excellent metal control in polychromatic finishes

## Polymer Type

- Solventborne Polyester

## Sales Specifications

Solid Content at 125°C, % (ISO 3251)	54 - 56
Viscosity at 25°C, mPa.s (ISO 12058-1)	1500 - 2500
Colour, Hazen scale (ISO 6271)	150 max
Acid value, mg KOH/g (ISO 2114)	12 max

## Other Characteristics<sup>1</sup>

Volatile	Xylene
Flash point, °C (ISO 3679)	24
Density / Specific Gravity at 20°C, g/ml (ISO 2811)	1.0
Hydroxyl Content, %	4.1
Hydroxyl Equivalent weight	415

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

<sup>1</sup> The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

## RECOMMENDATIONS FOR USE

SYNOCURE® 861 X 55 should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

$$\text{Hydroxyl equivalent weight} = \frac{17 \times 100}{\% \text{ OH}}$$

$$\text{Isocyanate equivalent weight} = \frac{42 \times 100}{\% \text{ NCO}}$$

Using Desmodur® N 75 series (1) or Tolonate™ HDB 75 MX (2), the recommended ratios would be:

	on solid resin	as supplied
SYNOCURE® 861 X 55	415	755
Desmodur® N 75 series (1) or Tolonate™ HDB 75 MX (2)	191	255

At normal temperatures, the surface drying time of paints based on this combination is typically 25 min, with hard dry in 75 min.

SYNOCURE® 861 X 55 reacted with Desmodur® N 75 series (1) or Tolonate™ HDB 75 MX (2) in stoichiometric proportions has a usable pot life at spraying viscosity in excess of a full working

## Formulation Guidelines

**SYNOCURE®**

day at normal room temperature. The use of catalysts or higher temperatures will reduce this storage period.

To increase the initial rate of cure of SYNOCURE® 861 X 55 paints, at both room temperature and under low bake conditions, the use of tin or zinc catalysts in the form of dibutyl tin dilaurate or zinc octoate is recommended. The levels used will depend on specific requirements, but typical metal contents calculated on total solid resin would be 0.001% tin or 0.0015% zinc.

#### SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 861 X 55 should be free of water and should not contain groups that react with isocyanates.

Esters and ketones are true solvents for this type of system and are recommended for use in conjunction with aromatic hydrocarbon diluents such as xylene.

#### OTHER ADDITIVES

Byk®-P 104 S (3) has been successfully used whenever a wetting agent has been necessary.

Suitable flow additives include Byk®-344 (3). There are also a number of polymeric additives which may be used for improving flow.

*Notes: (1) Bayer MaterialScience, (2) Vencorex Chemicals, (3) Byk*

---

## Product Safety

Please refer to the corresponding Safety Data Sheet.

---

## Storage & Handling

SYNOCURE® 861 X 55 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months from the shipping date

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Arkema has implemented a Medical Policy regarding the use of Arkema products in medical devices applications that are in contact with the body or circulating bodily fluids (<http://www.arkema.com/en/social-responsibility/responsible-product-management/medical-device-policy/index.html>) Arkema has designated medical grades to be used for such medical device applications. Products that have not been designated as medical grades are not authorized by Arkema for use in medical device applications that are in contact with the body or circulating bodily fluids. In addition, Arkema strictly prohibits the use of any Arkema products in medical device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days. The Arkema trademarks and the Arkema name shall not be used in conjunction with customers' medical devices, including without limitation, permanent or temporary implantable devices, and customers shall not represent to anyone else, that Arkema allows, endorses or permits the use of Arkema products in such medical devices.

It is the sole responsibility of the manufacturer of the medical device to determine the suitability (including biocompatibility) of all raw materials, products and components, including any medical grade Arkema products, in order to ensure that the final end-use product is safe for its end use; performs or functions as intended; and complies with all applicable legal and regulatory requirements (FDA or other national drug agencies). It is the sole responsibility of the manufacturer of the medical device to conduct all necessary tests and inspections and to evaluate the medical device under actual end-use requirements and to adequately advise and warn purchasers, users, and/or learned intermediaries (such as physicians) of pertinent risks and fulfill any postmarket surveillance obligations. Any decision regarding the appropriateness of a particular Arkema material in a particular medical device should be based on the judgment of the manufacturer, seller, the competent authority, and the treating physician.

### Arkema Coating Resins

420, rue d'Estienne d'Orves

92705 Colombes Cedex - France

arkema.com - [arkemacoatingresins.com](http://arkemacoatingresins.com)