

SYNOLAC[®] 9645S55

Saturated (Oil Free) Polyester

ARKEMA COATING RESINS

Product Application details SYNOLAC[®] 9645S55 is a linear oil free polyester developed for use in Coil Coating, sheet fed Metal Decorating and General Industrial applications.

Performance Benefits

- Excellent Flexibility
- Excellent hardness
- Good gloss
- Good durability

Polymer Type

- Solventborne Polyester

Sales Specifications

| | |
|--------------------------------------|---------|
| Solid Content at 125°C, % (ISO 3251) | 54 - 56 |
| Viscosity at 25°C, Gardner Holdt | Z1± |
| Colour, Gardner scale (ASTM D1544) | 3 max |
| Acid value, mg KOH/g (ISO 2114) | 3 max |

Other Characteristics¹

| | |
|---|-----------------------------|
| Volatile | Aromatic 150 / butyl glycol |
| Density / Specific Gravity at 25°C, g/ml (ISO 2811) | 1.06 |
| Hydroxyl Value, mg KOH/g | 16.5 |

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

RECOMMENDATIONS FOR USE

SYNOLAC[®] 9645S55 is compatible with a wide range of melamine resins and is typically used with hexamethoxymethyl melamine and partially methylated melamine. It is also compatible with alkyd, polyester, epoxy and partially in acrylic resin.

SYNOLAC[®] 9645S55 with hexamethoxymethyl melamine resin at ratio of 70:30 to 85:15 on solid resin content is suggested.

To promote cure, the use of between 1% and 5% of acid catalyst is recommended, e.g. paratoluene sulphonic acid, calculated on melamine solids.

Formulation Guidelines

Variation in levels of SYNOLAC[®] 9645S55 and the type of amino resin will modify the overall performance characteristics of the coating. Increasing the level of amino resin (and catalyst) will generally tend to increase the hardness and solvent resistance of the coating but may compromise flexibility.

For coil coating applications an 85:15 to 80:20 ratio, on solids, pTSA catalyst on amino level. For metal decorating formulations, a recommended blend, on solids, of 72:18:10 OFPE: melamine: epoxy resin (epoxy equ »500) with 2% pTSA solids amino is suitable.

Part methylated amino resin can be used in place of hexamethoxymethyl melamine and will develop very good hardness & solvent resistance but at the expense of flexibility.

Benzoguanamine resin can also be used to increase cure response and retortability.

SYNOLAC[®]

General industrial enamels can be formulated with 70:30 to 80:20 ratios with hexamethoxymethyl melamine or part methylated melamine, with 2% pTSA catalyst.

This resin can be used in combination with Isocyanates.

Enamels based on SYNOLAC® 9645S55 exhibit good light fastness results after prolonged UV exposure and finishes are resistant to staining from variety of household materials.

SOLVENTS

Mixtures of high boiling aromatic hydrocarbons, alcohols, glycol ethers esters and ketones are appropriate coating applications, aromatic hydrocarbons for Metal Decorating finishes and aromatic hydrocarbon/alcohol blends for General Industrial enamels.

Product Safety

Please refer to the corresponding Safety Data Sheet.

Storage & Handling

SYNOLAC® 9645S55 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be 12 months.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Arkema has implemented a Medical Policy regarding the use of Arkema products in medical devices applications that are in contact with the body or circulating bodily fluids (<http://www.arkema.com/en/social-responsibility/responsible-product-management/medical-device-policy/index.html>) Arkema has designated medical grades to be used for such medical device applications. Products that have not been designated as medical grades are not authorized by Arkema for use in medical device applications that are in contact with the body or circulating bodily fluids. In addition, Arkema strictly prohibits the use of any Arkema products in medical device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days. The Arkema trademarks and the Arkema name shall not be used in conjunction with customers' medical devices, including without limitation, permanent or temporary implantable devices, and customers shall not represent to anyone else, that Arkema allows, endorses or permits the use of Arkema products in such medical devices.

It is the sole responsibility of the manufacturer of the medical device to determine the suitability (including biocompatibility) of all raw materials, products and components, including any medical grade Arkema products, in order to ensure that the final end-use product is safe for its end use; performs or functions as intended; and complies with all applicable legal and regulatory requirements (FDA or other national drug agencies). It is the sole responsibility of the manufacturer of the medical device to conduct all necessary tests and inspections and to evaluate the medical device under actual end-use requirements and to adequately advise and warn purchasers, users, and/or learned intermediaries (such as physicians) of pertinent risks and fulfill any postmarket surveillance obligations. Any decision regarding the appropriateness of a particular Arkema material in a particular medical device should be based on the judgment of the manufacturer, seller, the competent authority, and the treating physician.

Arkema Coating Resins Malaysia Sdn Bhd

PL0 491, Jalan Keluli, Pasir Gudang Industrial Estate,

81700 Pasir Gudang, Johor, Malaysia.

arkema.com - arkemacoatingresins.com

