# SYNOLAC® N36X

SHORT OIL ALKYD ARKEMA COATING RESINS

## Product Application details

SYNOLAC® N36X is short oil, non-drying resin based on saturated fatty acids. It is well fitted as a backbone resin in acid curing and nitrocellulose finishes where excellent colour and colour stability is desired. Very good wet heat resistance can be attained when formulated with relevant amino resins.

### Performance Benefits

- Excellent light color
- Fast drying time
- Good hardness
- Good chemical resistant
- Good wet heat resistance
- Non-yellowing

### Polymer Type

Solventborne Alkyd

### Sales Specifications

Solid Content % (ISO 3251)	58 - 62
Viscosity at 25°C, Gardner Holdt	Z3 – Z4
Colour, Gardner scale (ASTM D1544)	
Acid value, mg KOH/g (ISO 2114)	9 - 11

### Other Characteristics<sup>1</sup>

Volatile	Xylene
Density / Specific Gravity at 25°C, g/ml (ISO 2811)	1.03
Type of fatty acid	Saturated Fatty Acid
Fatty Acid content, %	36
OH Value, % approx.	4.7

Note: Acid value and/or Hydroxyl value quoted relative to solid resin

### **RECOMMENDATIONS FOR USE**

SYNOLAC® N36X is recommended for premium quality acid curing, polyurethane and nitro-cellulose furniture wood coating. It is particularly recommended for higher solids, higher build and light colour coatings suited.

## Formulation Guidelines

#### **SOLUBILITY**

Aromatic hydrocarbon
Ester
Complete
Ketone
Glycol Ether
Alcohol
Aliphatic Hydrocarbon
Complete
Complete
Complete
Partial
Not Soluble



<sup>1</sup> The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

	<u>COMPATIBILITY</u>		
	Urea Resins	Very Good	
	Isocyanate Resins	Very Good	
	Short Oil Alkyd	Good	
	Melamine Resins	Good	
	NC/CAB	Good	
	Polyester Resins	Fair	
	Acrylic Resins	Fair	
	Epoxy Resins	Fair	
Product Safety	Please refer to the corresponding Safety Data Sheet.		
Storage & Handling	SYNOLAC® N36X should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided.		
	In the above mentioned storage conditions the shelf life of the resin will be 12 months.		

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Arkema expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations.

Arkema has implemented a Medical Policy regarding the use of Arkema products in medical devices applications that are in contact with the body or circulating bodily fluids (http://www.arkema.com/en/social-responsibility/responsible-product-management/medical-device-policy/index.html) Arkema has designated medical grades to be used for such medical device applications. Products that have not been designated as medical grades are not authorized by Arkema for use in medical device applications that are in contact with the body or circulating bodily fluids. In addition, Arkema strictly prohibits the use of any Arkema products in medical device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days. The Arkema trademarks and the Arkema name shall not be used in conjunction with customers' medical devices, including without limitation, permanent or temporary implantable devices, and customers shall not represent to anyone else, that Arkema allows, endorses or permits the use of Arkema products in such medical devices.

It is the sole responsibility of the manufacturer of the medical device to determine the suitability (including biocompatibility) of all raw materials, products and components, including any medical grade.

Arkema products, in order to ensure that the final end-use product is safe for its end use; performs or functions as intended; and complies with all applicable legal and regulatory requirements (FDA or other national drug agencies). It is the sole responsibility of the manufacturer of the medical device to conduct all necessary tests and inspections and to evaluate the medical device under actual end-use requirements and to adequately advise and warn purchasers, users, and/or learned intermediaries (such as physicians) of pertinent risks and fulfill any postmarket surveillance obligations. Any decision regarding the appropriateness of a particular Arkema material in a particular medical device should be based on the judgment of the manufacturer, seller, the competent authority, and the treating physician.

### Arkema Coating Resins Malaysia Sdn Bhd

PLO 491, Jalan Keluli, Pasir Gudang Industrial Estate, 81700 Pasir Gudang, Johor, Malaysia. arkema.com - arkemacoatingresins.com

