

TECHNICAL DATA SHEET

CHEMPOL® 211-2339

Oil free polyester

PRODUCT APPLICATION DETAILS

CHEMPOL® 211-2339 is a high solids polyester with excellent adhesion, exterior durability, and color retention, that provides flexibility in 2K urethane coatings. CHEMPOL® 211-2339 is compatible with thermoset acrylic resins and can be used as a modifier to reduce VOC.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	94 %	-
Viscosity	Z5-Z6+ Gardner Holdt	-
Reduced viscosity (70% in Xylene)	C-E	-
Color	2 Gardner	-
Acid value	6 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Density	9.3 lbs/gal	-
Hydroxyl content	0.3 %	-
Hydroxyl number	240	-

¹ The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry
 - Protective And Marine Coating

PERFORMANCE BENEFITS

- Excellent adhesion
- Good exterior durability
- Excellent color retention



Coating Resins - 2025-05-25 - Page: 2 / 2

CHEMPOL® 211-2339

FORMULATION GUIDELINES

RECOMMENDATIONS OF USE

Provides flexibility in 2K urethane coatings. Metal – General purpose high performance enamel. Modifier to reduce VOC.

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

CHEMPOL® 211-2339 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700 Headquarter: Arkema France 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

