

TECHNICAL DATA SHEET

CHEMPOL® 211-3369

Oil free polyester

PRODUCT APPLICATION DETAILS

CHEMPOL® 211-3369 is an economical coil polyester used in exterior coatings for structural steel and aluminum, and also for coatings for office furniture, light fixtures, and appliances.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	70 %	-
Viscosity	Z2-Z5 Gardner Holdt	-
Reduced viscosity (50% in Butoxyethanol)	J-M	-
Color	4 Gardner	-
Acid value	9 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	A150/Butoxyethanol/Xylene 75/18.5/6.5	-
Density	9.1 lbs/gal	-
Hydroxyl content	1.1 %	-
Hydroxyl equivalent weight	1600	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

- Coatings & Inks
- Industrial Coating
    - Coil

PERFORMANCE BENEFITS

- Structural Steel Coatings
- Aluminum Coatings
- Appliance Coatings
- Metal Office Furniture

# CHEMPOL® 211-3369

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

CHEMPOL® 211-3369 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarter: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790