

TECHNICAL DATA SHEET

CHEMPOL[®] 211-8915

Oil free polyester

PRODUCT APPLICATION DETAILS

CHEMPOL 211-8915 is a high performance polyester in exempt solvent for industrial, military, and aerospace coatings.

SALES SPECIFICATIONS

| | CHARACTERISTICS | METHODS |
|---------------|---------------------|---------|
| Solid content | 65 % | - |
| Viscosity | Z1-Z2 Gardner Holdt | - |
| Color | 9 Gardner | - |
| Acid value | 6 mg KOH/g | - |

OTHER CHARACTERISTICS¹

| | CHARACTERISTICS | METHODS |
|------------------|-----------------|---------|
| Solvent | t-BAc/Xylene | - |
| Density | 9 lbs/gal | - |
| Hydroxyl content | 2.2 % | - |
| Hydroxyl number | 72 | - |

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Automotive - OEM
 - General Industry
 - Protective And Marine Coating

CHEMPOL® 211-8915

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

CHEMPOL® 211-8915 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790