

TECHNICAL DATA SHEET

CHEMPOL® 317-0250

Thermoset acrylic

PRODUCT APPLICATION DETAILS

CHEMPOL® 317-0250 is a thermoset acrylic resin for use in air dry or force dry clears or gloss enamels, and in concrete sealers, that gives exterior durability, gloss and color retention, and resistance to oils, greases and chemical fumes.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	50%	-
Viscosity	Z1-Z2Gardner Holdt	-
Reduced viscosity(35% in Aromatic 100)	H-K	-
Color	60APHA	-
Acid value	2mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Aromatic 100	-
Density	8lbs/gal	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry

PERFORMANCE BENEFITS

- Good Exterior Durability
- Air Dry or Force Dry Clears or Gloss Enamels
- Concrete Sealers
- High Gloss and Color Retention
- Good Resistance to Oils, Greases and Chemical Fumes

CHEMPOL® 317-0250

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

CHEMPOL® 317-0250 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790