

TECHNICAL DATA SHEET

CHEMPOL® 317-2500

PRODUCT APPLICATION DETAILS

 $\hbox{CHEMPOL$^{\circledcirc}$ 317-2500 is an acrylic polyol designed for either 2K urethane or thermoset}$ applications with good flexibility, impact resistance, color retention, and adhesion.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	60 %	-
Viscosity	Z1-Z3 Gardner Holdt	-
Color	1 Gardner	-
Acid value	12 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene/PM Acetate 75/25	-
Density	8.64 +/- 0.1 lbs/gal	-
Hydroxyl equivalent weight	330	-
Hydroxyl number	170	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- · Industrial Coating

 - Automotive OEMAutomotive Refinish
 - Protective And Marine Coating

PERFORMANCE BENEFITS

- Outstanding Exterior Durability in 2K Urethanes
- Very Good Flexibility
- Very Good Impact Resistance
- Excellent Color Retention
- Very Good Adhesion



Coating Resins - 2025-02-01 - Page: 2 / 2

CHEMPOL® 317-2500

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

CHEMPOL® 317-2500 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700 **Headquarter: Arkema France** 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

