

## TECHNICAL DATA SHEET

# CHEMPOL® 801-0066

*Solventborne Alkyd*

### PRODUCT APPLICATION DETAILS

CHEMPOL® 801-0066 is solvent-free soya-based long oil alkyd.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	99+ %	-
Viscosity	Z1-Z3 Gardner Holdt	-
Color	7 Gardner	-
Acid value	10 mg KOH/g	-

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Density	8,5 lbs/gal	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Architectural Coating
  - Exterior Wall
  - Specialty Coatings
  - Stains
  - Trim
- Flooring
  - Floor Polish & Floor Coatings

# CHEMPOL® 801-0066

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

CHEMPOL® 801-0066 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarter: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790