

TECHNICAL DATA SHEET

CHEMPOL[®] 801-6050

Solventborne Alkyd

PRODUCT APPLICATION DETAILS

CHEMPOL[®] 801-6050 is a flexible linoleic long oil alkyd for air-dry systems.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	65 %	-
Viscosity	Y-Z1 Gardner Holdt	-
Color	7 Gardner	-
Acid value	10 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Mineral spirits/A100	-
Density	7.8 lbs/gal	-
Hydroxyl content	1.8 %	-
Hydroxyl number	59	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Exterior Wall
 - Primers
 - Specialty Coatings
 - Stains
 - Trim
- Flooring
 - Floor Polish & Floor Coatings

CHEMPOL® 801-6050

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

CHEMPOL® 801-6050 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA