

### TECHNICAL DATA SHEET

# CHEMPOL® 802-3515

Medium oil alkyd

### **PRODUCT APPLICATION DETAILS**

CHEMPOL® 802-3515 is a cost-effective medium oil soya alkyd with fast set times, high hardness, and good gloss and color retention, for use in metal primers and coatings, and traffic paints.

### **SALES SPECIFICATIONS**

	CHARACTERISTICS	METHODS
Solid content	50 %	-
Viscosity	Z1-Z3 Gardner Holdt	-
Reduced viscosity (40% in VM&P)	E-H Gardner Holdt	-
Color	7 Gardner	-
Acid value	12 mg KOH/g	-

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	VM&P/Xylene	-
Density	7.4 lbs/gal	-
Hydroxyl content	1.9 %	-
Hydroxyl number	64	-

<sup>&</sup>lt;sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### **MARKETS**

### **Coatings & Inks**

- Industrial Coating
  - General Industry

### **PERFORMANCE BENEFITS**

- Fast set times
- Compatible with a wide range of alkyds
- Economical
- High hardness & toughness
- Good gloss and color retention
- Meets federal specification TT-P-115c, Type1



# Coating Resins - 2025-04-25 - Page: 2 / 2

## CHEMPOL® 802-3515

### **FORMULATION GUIDELINES**

### **RECOMMENDATIONS OF USE**

Auto Refinish Metal–Primer Coatings Agricultural Coatings Traffic Paint

### **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

### **STORAGE AND HANDLING**

CHEMPOL® 802-3515 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700 **Headquarter: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

