

TECHNICAL DATA SHEET

CHEMPOL[®] 803-4084

Short Oil Alkyd

PRODUCT APPLICATION DETAILS

CHEMPOL[®] 803-4084 is a high solids short oil TOFA baking alkyd with high hardness and low temperature cure, for use in metal coatings.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	90+ %	-
Viscosity	Z4-Z6 Gardner Holdt	-
Reduced viscosity (70% in n-Butyl Acetate)	D-G Gardner Holdt	-
Color	10 Gardner	-
Acid value	15 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Density	9.23 lbs/gal	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry

PERFORMANCE BENEFITS

- Rapid Viscosity Reduction
- High Hardness
- Low Temperature Cure
- Good Compatibility

CHEMPOL® 803-4084

FORMULATION GUIDELINES

RECOMMENDATIONS OF USE

Metal Furniture Coatings
Structural steel coatings
General Industrial Metal

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

CHEMPOL® 803-4084 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA