

TECHNICAL DATA SHEET

CHEMPOL® 809-3068

PRODUCT APPLICATION DETAILS

CHEMPOL® 809-3068 is a chain-stopped soya short oil alkyd with high gloss, superior gloss retention, and excellent salt spray resistance, for use in 2K urethane metal coatings.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	50 %	-
Viscosity	T-W Gardner Holdt	-
Reduced viscosity (40% in Xylene)	B-D	-
Color	8 Gardner	-
Acid value	12 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Density	8.3 lbs/gal	-
Hydroxyl content	3.5 %	-
Hydroxyl equivalent weight	480	-
Hydroxyl number	117	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Automotive - OEM
 - General Industry

PERFORMANCE BENEFITS

- High gloss
- Superior Florida gloss retention
- Good salt spray resistance
- Excellent resin for alkyd 2K urethane coatings

CHEMPOL® 809-3068

FORMULATION GUIDELINES

RECOMMENDATIONS OF USE

Agricultural and heavy equipment coatings
Transportation finishes
General industrial metal
Machinery enamels

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

CHEMPOL® 809-3068 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790