# **CHEMPOL**<sup>®</sup>

## TECHNICAL DATA SHEET CHEMPOL<sup>®</sup> 809-3132

## **PRODUCT APPLICATION DETAILS**

CHEMPOL® 809-3132 is a high solids chain-stopped soya/DCO short oil alkyd with fast surface dry times, superior gloss retention, and excellent early water spot resistance, for use in 2K urethane metal coatings.

## **SALES SPECIFICATIONS**

	CHARACTERISTICS	METHODS
Solid content	75 %	-
Viscosity	Z3-Z5 Gardner Holdt	-
Reduced viscosity (60% in Xylene)	J-L	-
Color	8 Gardner	-
Acid value	10 mg KOH/g	-

## **OTHER CHARACTERISTICS<sup>1</sup>**

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Density	8.8 lbs/gal	-
Hydroxyl content	1.9 %	-
Hydroxyl equivalent weight	876	-
Hydroxyl number	64	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS Coatings & Inks

Industrial Coating

- Automotive OEM
- General Industry

## **PERFORMANCE BENEFITS**

- Fast surface dryGood early water spot
- resistanceExcellent Florida gloss
- Excellent Florida gloss retention
- May be forced dried
  Excellent resin for alkyd 2K urethane coatings



## **CHEMPOL® 809-3132**

## FORMULATION GUIDELINES

#### **RECOMMENDATIONS OF USE**

Agricultural and Heavy Equipment coatings Transportation finishes General Industrial metal **Machinery Enamels** 

## **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

### **STORAGE AND HANDLING**

CHEMPOL® 809-3132 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Coating Resins - 2025-05-25 - Page: 2 / 2

**Arkema Coating Resins** 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

**Headquarter: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

ARKEMA

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof. Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the

number 319 632 790

arkema.com