

TECHNICAL DATA SHEET

CHEMPOL® 809-8068

PRODUCT APPLICATION DETAILS

CHEMPOL® 809-8068 is a chain-stopped soya short oil alkyd with high gloss, superior gloss retention, and excellent salt spray resistance, for use in 2K urethane metal coatings. CHEMPOL® 809-8068 is the t-butyl acetate version of CHEMPOL® 809-3068.

SALES SPECIFICATIONS

| | CHARACTERISTICS | METHODS |
|---|---------------------|---------|
| Solid content | 60 % | - |
| Viscosity | Z1-Z3 Gardner Holdt | - |
| Reduced viscosity (40% in Butyl Acetate) | A-C | - |
| Color | 8 Gardner | - |
| Acid value | 12 mg KOH/g | - |

OTHER CHARACTERISTICS¹

| | CHARACTERISTICS | METHODS |
|----------------------------|-----------------|---------|
| Solvent | t-Butyl acetate | - |
| Density | 8.6 lbs/gal | - |
| Hydroxyl content | 3.2 % | - |
| Hydroxyl equivalent weight | 524 | - |
| Hydroxyl number | 107 | - |

^{&#}x27;The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry

PERFORMANCE BENEFITS

- High gloss
- Superior Florida gloss retention
- Good salt spray resistance
- Excellent resin for alkyd 2K urethane coatings



Coating Resins - 2025-02-01 - Page: 2 / 2

CHEMPOL® 809-8068

FORMULATION GUIDELINES

RECOMMENDATIONS OF USE

Agricultural and heavy equipment coatings Transportation finishes General industrial metal Machinery enamels

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

CHEMPOL® 809-8068 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700 Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

