

TECHNICAL DATA SHEET

CHEMPOL® 812-5219

Modified alkyd

PRODUCT APPLICATION DETAILS

CHEMPOL® 812-5219 is a high solids rosin-modified alkyd with fast air-dry times and good adhesion, for use in primers.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	75 %	-
Color	14 Gardner	-
Acid value	22 mg KOH/g	-

OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Hydroxyl content	1.5 %	-
Hydroxyl number	50	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
  - General Industry

PERFORMANCE BENEFITS

- Fast Air Dry
- Good Adhesion
- Fast Sand Time

# CHEMPOL® 812-5219

## FORMULATION GUIDELINES

### RECOMMENDATIONS OF USE

Primers

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

CHEMPOL® 812-5219 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarter: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

