

TECHNICAL DATA SHEET

ENCOR[®] 309

Vinyl Emulsion

PRODUCT APPLICATION DETAILS

High molecular weight vinyl-acrylic latex designed for architectural coatings where high scrub resistance and exterior durability are of primary importance.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	55.0 %	-
pH	4.5 - 5.5	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV)	<500 cP	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Minimum film formation temperature	12 °C	-
Glass transition temperature (DSC)	19 °C	-
Density	9	-
Average particle size	300 nm	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Exterior Wall
 - Interior Wall
 - Primers
 - Trim

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

ENCOR® 309 - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80