

TECHNICAL DATA SHEET

ENCOR® 3130

Acrylic dispersion

PRODUCT APPLICATION DETAILS

ENCOR® 3130 is an acrylic copolymer emulsion, self-crosslinking at room temperature. This product is free from APE surfactants.

ENCOR® 3130 is mainly used in basecoat compositions, for different kinds of leather and splits, providing excellent softness and embossing resistance.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (105°C)	49 - 51 %	ISO 3251
рН	7.5 - 8.5	ISO 976
Viscosity (Brookfield RVT, 100rpm, sp2) (23°C)	50 - 250 mPa.s	ISO 2555

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Stabilizing system	A / NI	-
Minimum film formation temperature	< 5 °C	ISO 2115
Glass transition temperature (DSC)	- 12 °C	-
Density (23°C)	1.04 g/ml	ISO 2811
Average particle size	170 nm	ISO 13321

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Textile & Leather Coating
 - Leather

PERFORMANCE BENEFITS

- Soft film, characterized by a good elasticity
- High covering effect on embossed leather
- Good mechanical and solvent resistance



ENCOR® 3130

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

ENCOR® 3130 should be stored indoors in the original, unopened and undamaged container, in a dry place at storage temperatures between 5°C and 30°C. Exposure to direct sunlight should be avoided. The product is protected to prevent any microbial deterioration during normal conditions of storage but care should be taken to avoid accidental contamination during subsequent handling and processing. In the above mentioned storage conditions the shelf life of the resin will be from the shipping date. Shelf Life Durability (Months): 6

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

