

TECHNICAL DATA SHEET

ENCOR® 446

PRODUCT APPLICATION DETAILS

Latex for construction adhesives with good binding capability

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	62.0 %	-
рН	6.0	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV) (25+/-2 °C)	550 cP	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Minimum film formation temperature	6 °C	-
Glass transition temperature (DSC)	12 °C	-
Density	8.8	-
Average particle size	300 nm	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Building & Construction

- Construction Materials
 - Cement Modifier



ENCOR® 446

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

ENCOR® 446 - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700 **Headquarter: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

