

# TECHNICAL DATA SHEET

# ENCOR® 4516

Acrylic Emulsion

#### **PRODUCT APPLICATION DETAILS**

 ${\tt ENCOR}^{\circ}$  4516 is a high solids pure acrylic binder, free from solvents, plasticizers and APE surfactants.

ENCOR® 4516 is ideally suited for the formulation of low emission floor covering adhesives, compliant with Emicode EC1 classification.

Due to its specific composition,  $ENCOR^{\circ}$  4516 allows to produce glues for different types of floor covers such as PVC, linoleum, rubber and carpet.

## **SALES SPECIFICATIONS**

|   | CHARACTERISTICS   | METHODS  |
|---|-------------------|----------|
| Solid content (105°C)                     | 59 - 61 %         | ISO 3251 |
| рН  | 7.0 - 8.0         | ISO 976  |
| Viscosity (Brookfield RVT , 20rpm) (23°C) | 1000 - 3000 mPa.s | ISO 2555 |

#### OTHER CHARACTERISTICS<sup>1</sup>

|                                    | CHARACTERISTICS | METHODS   |
|------------------------------------|-----------------|-----------|
| Stabilizing system                 | A/NI            | -         |
| Minimum film formation temperature | < 1 °C          | ISO 2115  |
| Glass transition temperature (DSC) | -27 °C          | -         |
| Density (23°C)                     | 1.03 g/ml       | ISO 2811  |
| Average particle size              | 450 nm          | ISO 13321 |

<sup>&</sup>lt;sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

#### **MARKETS**

#### **Building & Construction**

- Construction Materials
  - Flexible Flooring Adhesives

## **PERFORMANCE BENEFITS**

- High solids
- Allows the formulation of Emicode EC1 compliant glues



# **ENCOR® 4516**

#### **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

#### **STORAGE AND HANDLING**

ENCOR® 4516 should be stored indoors in the original, unopened and undamaged container, in a dry place at storage temperatures between 5°C and 30°C. Exposure to direct sunlight should be avoided. The product is protected to prevent any microbial deterioration during normal conditions of storage but care should be taken to avoid accidental contamination during subsequent handling and processing. In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Shelf Life (Months): 6

**Headquarter: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

