

### TECHNICAL DATA SHEET

# ENCOR® 627

Acrylic Emulsion

#### **PRODUCT APPLICATION DETAILS**

Binder that effectively blocks stains from substrates that tend to exude tannins, and is effective in stain-blocking primers, masonry primers, and wood stains.

#### **SALES SPECIFICATIONS**

|                                                   | CHARACTERISTICS | METHODS |
|---------------------------------------------------|-----------------|---------|
| Solid content                                     | 43.5 %          | -       |
| рН                                                | 7.5             | -       |
| Viscosity (#3 spindle @ 60 rpm.<br>Brookfield LV) | 550 cP          | -       |

#### **OTHER CHARACTERISTICS<sup>1</sup>**

|                                    | CHARACTERISTICS | METHODS |
|------------------------------------|-----------------|---------|
| Minimum film formation temperature | 9 °C            | -       |
| Glass transition temperature (DSC) | 15 °C           | -       |
| Density                            | 8.8             | -       |
| Average particle size              | 100 nm          | -       |

<sup>&#</sup>x27;The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

#### **MARKETS**

#### **Coatings & Inks**

- · Architectural Coating
  - Exterior Wall
  - Interior Wall
  - Primers
  - Specialty Coatings Trim



## **ENCOR® 627**

#### **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

#### **STORAGE AND HANDLING**

ENCOR® 627 - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700 **Headquarter: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

