

TECHNICAL DATA SHEET ENCOR® FLEX 192

PRODUCT APPLICATION DETAILS

For ASTM D-6083 Type 1 Spec, with excellent adhesion to aged TPO

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	61.0 %	-
рН	8.0	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV) (25+/-2 °C)	500 cP	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Minimum film formation temperature	0 °C	-
Glass transition temperature (DSC)	-21 °C	-
Density	8.7	-
Average particle size	350 nm	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Building & Construction

Construction Materials
Elastomeric Roof



ENCOR® FLEX 192

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

ENCOR® FLEX 192 - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.

Coating Resins - 2025-03-08 - Page: 2 / 2

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex - France T +33 (0)1 49 00 80 80

ARKEMA

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof. Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the

number 319 632 790

arkema.com