

## TECHNICAL DATA SHEET

# NEOCAR<sup>®</sup> Acrylic 850

### PRODUCT APPLICATION DETAILS

NEOCAR<sup>®</sup> Acrylic 850 is an ultra-small particle size, hydrophobic latex with ambient cross-linking. For further information please contact Arkema.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	45 %	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV) (25+/-2 °C)	150 cP	-

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Minimum film formation temperature	45 °C	-
Glass transition temperature (DSC)	50 °C	-
Density	8.7	-
Average particle size	70 nm	-

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Architectural Coating
  - Exterior Wall
  - Interior Wall
  - Specialty Coatings
- Textile & Leather Coating
  - Non Woven

#### Building & Construction

- Construction Materials
  - Flooring

# NEOCAR® ACRYLIC 850

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

NEOCAR® Acrylic 850 - When storing and handling follow procedures recommended for polymer dispersions. Use corrosion resistant storage tanks and piping. Air-operated diaphragm pumps are preferred. Avoid temperature extremes. Do not freeze. Store between 40 to 90 °F (4 -32 °C). Packaged material should be stored indoors in a dry place in the original unopened and undamaged container. Exposure to direct sunlight should be avoided. The product is protected to prevent microbial deterioration during normal storage conditions; however, care should be taken to avoid accidental contamination during subsequent handling and processing. Bulk storage and handling practices are described in the Arkema Latex Storage and Handling Guide. For a copy of this guide contact Arkema.  
Shelf Life (Months): 6

<b>Arkema Coating Resins</b> 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700	<b>Headquarter: Arkema France</b> 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80
--	---

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790