

TECHNICAL DATA SHEET

REAFREE® 2776-TS

Powder Resins / Saturated Carboxylated Polyester/ Glycidyl Ester

PRODUCT APPLICATION DETAILS

Saturated carboxylated polyester suitable for the formulation of outdoor durable and protective tribochargeable thermosetting powders in combination with Araldite PT-910 or PT-912 type hardeners. Polyester for pigmented and clear coats. Gas oven stabilised. TMA free type.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Acid value	23-28 mg KOH/g	ASTM D-1639
Viscosity (Cone and plate - 165°C)	50-90 Pa.s	DIN 53229
Color (50%)	2 max Gardner	ASTM D-1544

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Appearance	Pale granules	
Glass transition temperature (Tg)	approx 67 °C	DSC

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

CURING CONDITIONS

20 minutes at 170°C (object temperature)

RECOMMENDED MIXING RATIO

REAFREE® 2776-TS / Araldite® PT-910⁽¹⁾ : 93/7

⁽¹⁾ Huntsman

MARKET

Coatings & Inks

- Industrial Coating
 - General Industry
 - Metal Exterior - Powder

PERFORMANCE BENEFITS

- Good flow
- High gloss
- Good mechanical properties
- Good outdoor durability
- Excellent over-bake resistance, also in gas oven applications
- Excellent transparency in clear coats
- Tribochargeable

REAFREE® 2776-TS

FORMULATION GUIDELINES

	STARTING FORMULATION	
	Paint	Clear Coat
REAFREE® 2776-TS	594	844
Titanium Dioxide ⁽¹⁾	271	-
Barium Sulfate ⁽²⁾	53	-
Araldite PT-910 ⁽³⁾	44	71
REAFREE® F3300-A15	35	-
REAFREE® F4700-B10	-	80
Benzoin	3	5

⁽¹⁾ Kronos® 2160

⁽²⁾ Minerals Girona

⁽³⁾ Huntsman

APPLICATION / EXTRUSION CONDITIONS

	CHARACTERISTICS
Extruder	BUSS PCS-30
Spraying gun	GEMA PG 1-B
Torque	40 %
Extrusion speed	200 rpm
Application voltage	60-80 kV
Test substrate (Degreased steel)	1 mm
Extrusion temperature	105 °C

COATING PROPERTIES

	CHARACTERISTICS	METHODS
Film thickness	60-80 microns	
Gloss (60°)	Over 94 %	
Cupping test	Over 8 mm	DIN 53156
Direct impact	Over 80 kg.cm	ASTM D-2794
Reverse impact	Over 80 kg.cm	ASTM D-2794
Conical mandrel	100 %	ASTM D-522
Adhesion	Gt0	DIN 53151

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

DELIVERY FORM

Granules. White opaque polyethylene bags of 25 Kg. One Ton pallet shrink – wrapped.

STORAGE AND HANDLING

The resin in its original unopened bags is stable for more than three years, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Arkema Química, S.A.U.
Ctra. Olzinelles, s/n
E-08470 Sant Celoni (BCN)
Spain
T +34 938 674 000

Arkema Chemical India Private Ltd.
D-43, Trans Thane Creek
MIDC Industrial Area
400706 Mumbai - India
T +91 22 67377122

Headquarters: **Arkema France**
420, rue d'Estienne d'Orves
92705 Colombes Cedex
France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

ARKEMA