

## TECHNICAL DATA SHEET

# REAFREE® 4763-S

*Powder Resins / Saturated Carboxylated Polyester / TGIC*

### PRODUCT APPLICATION DETAILS

Saturated carboxylated polyester for combination with Triglycidylisocyanurate. Suitable for the formulation of outdoor durable and protective thermosetting powders for electrostatic application. Possibility to cure 1 minute / 290°C. High reactivity with good flexibility. Gas oven stabilized. TMA free type.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Acid value	30-36 mg KOH/g	ASTM D-1639
Viscosity (Cone and plate - 165°C)	15-25 Pa.s	DIN 53229
Color (50%)	2 max Gardner	ASTM D-1544

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Appearance	Pale granules	
Glass transition temperature (Tg)	approx 61 °C	DSC

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### CURING CONDITIONS

15 minutes at 160°C (object temperature)  
1 minute at 290°C (object temperature)

### RECOMMENDED MIXING RATIO

REAFREE® 4763-S / TGIC: 93/7

### MARKET

#### Coatings & Inks

- Industrial Coating
  - Coil
  - General Industry
  - Metal Exterior - Powder

### PERFORMANCE BENEFITS

- Excellent flexibility. Coil-coatings, PCM applications.
- Very good flow for high reactive type.
- High gloss.
- Good mechanical properties.
- Excellent outdoor durability.
- Reduced blooming at low temperature curing.

# REAFREE® 4763-S

## FORMULATION GUIDELINES

STARTING FORMULATION	
REAFREE® 4763-S	595
Titanium Dioxide <sup>(1)</sup>	320
Triglycidylisocyanurate <sup>(2)</sup>	45
REAFREE® F3300-A15	37
Benzoin	3

<sup>(1)</sup> Kronos® 2160  
<sup>(2)</sup> Araldite® PT-810 (Huntsman) / Tepic (Nissan Chemical)

## APPLICATION / EXTRUSION CONDITIONS

CHARACTERISTICS	
Extruder	BUSS PCS-30
Spraying gun	GEMA PG 1-B
Torque	40 %
Extrusion speed	200 rpm
Application voltage	60-80 kV
Test substrate (Degreased steel)	1 mm
Extrusion temperature	80 °C

## COATING PROPERTIES

	CHARACTERISTICS	METHODS
Film thickness	60-80 microns	
Gloss (60°)	Over 90 %	
Cupping test	Over 8 mm	DIN 53156
Direct impact	Over 80 kg.cm	ASTM D-2794
Reverse impact	Over 80 kg.cm	ASTM D-2794
Conical mandrel	100 %	ASTM D-522
Adhesion	Gt0	DIN 53151

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## DELIVERY FORM

Granules. White opaque polyethylene bags of 25 Kg. One Ton pallet shrink – wrapped.

## STORAGE AND HANDLING

The resin in its original unopened bags is stable for more than three years, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

<b>Arkema Coating Resins</b> 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700	<b>Arkema Química, S.A.U.</b> Ctra. Olzinelles, s/n E-08470 Sant Celoni (BCN) Spain T +34 938 674 000	<b>Arkema Chemical India Private Ltd.</b> D-43, Trans Thane Creek MIDC Industrial Area 400706 Mumbai – India T +91 22 67377122	<b>Headquarter: Arkema France</b> 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80
--	---	--	---

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790