

TECHNICAL DATA SHEET

REAFREE® 8585-T

Powder Resins / Saturated Carboxylated Polyester / β -Hydroxyalkylamide

PRODUCT APPLICATION DETAILS

Saturated carboxylated polyester for combination with β -Hydroxyalkylamide type hardeners. Suitable for the formulation of outdoor durable and protective tribochargeable thermosetting powders for electrostatic application. For high gloss systems with improved flow and degassing properties. Gas oven stabilised. TMA free type.

SALES SPECIFICATIONS

| | CHARACTERISTICS | METHODS |
|------------------------------------|-----------------|-------------|
| Acid value | 28-34 mg KOH/g | ASTM D-1639 |
| Color (50%) | 2 max Gardner | ASTM D-1544 |
| Viscosity (Cone and plate - 165°C) | 14-24 Pa.s | DIN 53229 |

OTHER CHARACTERISTICS¹

| | CHARACTERISTICS | METHODS |
|-----------------------------------|-----------------|---------|
| Appearance | Pale granules | |
| Glass transition temperature (Tg) | approx 58 °C | DSC |

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

CURING CONDITIONS

12 minutes at 180°C (object temperature)

RECOMMENDED MIXING RATIO

REAFREE® 8585-T / PRIMID XL-552 ⁽¹⁾: 95/5

REAFREE® 8585-T / PRIMID QM-1260 ⁽¹⁾: 94,5/5,5

⁽¹⁾ EMS-Chemie AG

MARKET

Coatings & Inks

- Industrial Coating
 - General Industry
 - Metal Exterior - Powder

PERFORMANCE BENEFITS

- Excellent flow and degassing properties
- High gloss
- Good mechanical properties
- Excellent outdoor durability
- Good yellowing resistance curing with direct-fired gas ovens
- Tribochargeable

REAFREE® 8585-T

FORMULATION GUIDELINES

| STARTING FORMULATION | |
|------------------------------------|-----|
| REAFREE® 8585-T | 564 |
| Titanium Dioxide ⁽¹⁾ | 310 |
| β-Hydroxyalkylamide ⁽²⁾ | 29 |
| REAFREE® F3300-R10 | 75 |
| Benzoin | 2 |
| CRAYVALLAC® PC | 10 |
| CRAYVALLAC® WN-1265 | 10 |

⁽¹⁾ Kronos® 2160
⁽²⁾ Primid® XL-552 (EMS Chemie)

APPLICATION / EXTRUSION CONDITIONS

| CHARACTERISTICS | |
|----------------------------------|-------------|
| Extruder | BUSS PCS-30 |
| Spraying gun | GEMA PG 1-B |
| Torque | 40 % |
| Extrusion temperature | 105 °C |
| Extrusion speed | 200 rpm |
| Application voltage | 60-80 kV |
| Test substrate (Degreased steel) | 1 mm |

COATING PROPERTIES

| | CHARACTERISTICS | METHODS |
|-----------------|-----------------|-------------|
| Adhesion | Gt0 | DIN 53151 |
| Film thickness | 60-80 microns | |
| Gloss (60°) | Over 90 % | |
| Cupping test | Over 8 mm | DIN 53156 |
| Direct impact | Over 80 kg.cm | ASTM D-2794 |
| Reverse impact | Over 80 kg.cm | ASTM D-2794 |
| Conical mandrel | 100 % | ASTM D-522 |

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

DELIVERY FORM

Granules. White opaque polyethylene bags of 25 Kg. One Ton pallet shrink – wrapped.

STORAGE AND HANDLING

The resin in its original unopened bags is stable for more than three years, stored in a dry place at temperature below 30°C. Avoid direct sunlight.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Arkema Química, S.A.U.
Ctra. Olzinelles, s/n
E-08470 Sant Celoni (BCN)
Spain
T +34 938 674 000

Arkema Chemical India Private Ltd.
D-43, Trans Thane Creek
MIDC Industrial Area
400706 Mumbai – India
T +91 22 67377122

Headquarters: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex
France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

ARKEMA