

### TECHNICAL DATA SHEET

# SNAP® 720

Acrylic Emulsion

#### **PRODUCT APPLICATION DETAILS**

Binder that offers outstanding block resistance in low or zero VOC high-gloss coatings, and is an excellent choice for low odor systems.

#### **SALES SPECIFICATIONS**

	CHARACTERISTICS	METHODS
Solid content	49.0 %	-
рН	7.0	-
Viscosity (#3 spindle @ 60 rpm. Brookfield LV)	<500 cP	-

#### **OTHER CHARACTERISTICS<sup>1</sup>**

	CHARACTERISTICS	METHODS
Minimum film formation temperature	<5 °C	-
Density	8.9	-
Average particle size	80 nm	-

<sup>&#</sup>x27;The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

#### **MARKETS**

#### **Coatings & Inks**

- Architectural Coating
  - Exterior Wall
  - Interior Wall
  - Specialty Coatings
  - Stains
  - Trim
- Flooring
  - Floor Polish & Floor Coatings



## **SNAP® 720**

#### **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

#### **STORAGE AND HANDLING**

SNAP® 720 should be stored indoors in the original, unopened and undamaged container, in a dry place at storage temperatures between 5°C and 30°C. Exposure to direct sunlight should be avoided. The product is protected to prevent any microbial deterioration during normal conditions of storage but care should be taken to avoid accidental contamination during subsequent handling and processing. In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700 **Headquarter: Arkema France** 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

