

TECHNICAL DATA SHEET

SYNOCURE® 865 EEP 70

Acrylic polyol

PRODUCT APPLICATION DETAILS

SYNOCURE® 865 EEP 70 is a hydroxy functional acrylic resin developed for use in two component systems requiring higher application solids. SYNOCURE® 865 EEP 70 has exceptional resistance to exposure to weather and UV light. Coatings based on SYNOCURE® 865 EEP 70 have excellent durability and gloss retention, a feature normally associated with higher hydroxyl content acrylics which are consequently more expensive to use. It is particularly suitable to high quality topcoats for Protective coatings also ACE and Vehicle Refinishing.

SALES SPECIFICATIONS

| | CHARACTERISTICS | METHODS |
|-----------------------|-------------------|----------|
| Solid content (125°C) | 68 - 72 % | ISO 3251 |
| Viscosity (25°C) | 4000 - 6000 mPa.s | ISO 3219 |
| Color | 50 max Hazen | ISO 6271 |
| Acid value | 8 max mg KOH/g | ISO 2114 |

OTHER CHARACTERISTICS¹

| | CHARACTERISTICS | METHODS |
|----------------------------|--------------------------|----------|
| Solvent | Ethyl-3-ethoxypropionate | - |
| Flash point | 41 °C | ISO 3679 |
| Density | 1.09 g/ml | ISO 2811 |
| Hydroxyl content | 3.1 % | - |
| Hydroxyl equivalent weight | 550 | - |

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Automotive - Refinish
 - General Industry
 - Protective And Marine Coating

PERFORMANCE BENEFITS

- Excellent exterior durability
- Good gloss, flow and DOI
- Good drying times

SYNOCURE® 865 EEP 70

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOCURE® 865 EEP 70 should be mixed just prior to application with the selected polyisocyanate. The mixing ratio is not critical although it is preferable to use stoichiometric ratios to obtain optimum performance.

SYNOCURE® 865 EEP 70 reacted with Desmodur® N 3390 series ⁽¹⁾, Desmodur® N 75 series ⁽¹⁾, Tolonate™ HDT-LV 2 or Tolonate™ HDB 75 MX ⁽²⁾ in stoichiometric proportions has a usable pot life at spraying viscosity in excess of a full working day at normal room temperature. Although the use of catalysts or higher temperatures will reduce this storage period, paints will still remain usable for many hours.

To increase the initial rate of cure of SYNOCURE® 865 EEP 70 based paints, at both ambient temperature and under low bake conditions, the use of tin catalyst in the form of dibutyl tin dilaurate is strongly recommended. The level used will depend on specific requirements, but the recommended minimum level would be 0.001% tin calculated on total solid resin plus isocyanate.

The reaction ratio is calculated from the respective equivalent weight or hydroxyl and isocyanate content of the reactants. The relationship is:

Hydroxyl Equivalent Weight = $(17 \times 100) / \%OH$

Isocyanate Equivalent Weight = $(42 \times 100) / \%NCO$

Using Desmodur® N 3390 series ⁽¹⁾, Desmodur® N 75 series ⁽¹⁾, Tolonate™ HDT-LV2 ⁽²⁾ or Tolonate™ HDB 75 MX ⁽²⁾, the recommended ratios would be:

- on solid resins: SYNOCURE® 865 EEP 70/Desmodur® N 3390 series ⁽¹⁾, Desmodur® N 75 series ⁽¹⁾, Tolonate™ HDT-LV2 ⁽²⁾ or Tolonate™ HDB 75 MX ⁽²⁾ = 550/191 or 183

- as supplied: SYNOCURE® 865 EEP 70/Desmodur® N 3390 series ⁽¹⁾, Desmodur® N 75 series ⁽¹⁾, Tolonate™ HDT-LV2 ⁽²⁾ or Tolonate™ HDB 75 MX ⁽²⁾ = 786/212 or 255 or 183

SOLUBILITY

The solvents chosen for paints and lacquers based on SYNOCURE® 865 EEP 70 should be free of water and should not contain groups that react with isocyanates. Esters and ketones are true solvents for this type of system and are recommended for use in conjunction with aromatic hydrocarbon diluents such as xylene.

Notes: ⁽¹⁾ Bayer MaterialScience, ⁽²⁾ VENCOREX® Chemicals

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOCURE® 865 EEP 70 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Shelf Life (Months): 12

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790