

### TECHNICAL DATA SHEET

# SYNOCURE® 9485 S 70

### **PRODUCT APPLICATION DETAILS**

SYNOCURE® 9485 S 70 is an acrylic for use in topcoats where a non-isocyanate (NISO) curing system is needed, that has exterior durability, solvent resistance, hardness, adhesion, and color retention. Long pot lie. Very high gloss. Requires primer where good corrosion resistance is needed.

### **SALES SPECIFICATIONS**

	CHARACTERISTICS	METHODS
Solid content	70 %	-
Viscosity	Z3-Z5 Gardner Holdt	-
Reduced viscosity (50% In Xylene)	F-I	
Color	6 Gardner	-
Acid value	18 mg KOH/g	-

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Xylene/PGMME 80/20	-
Glass transition temperature (DSC)	28 °C	-
Density	8.5 lbs/gal	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### **MARKETS**

### **Coatings & Inks**

- Industrial Coating
  - Automotive OEM
  - General Industry
  - Protective And Marine Coating



# Coating Resins - 2025-05-25 - Page: 2 / 2

## **SYNOCURE® 9485 S 70**

### **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

### **STORAGE AND HANDLING**

SYNOCURE® 9485 S 70 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided. In the above mentioned storage conditions the shelf life of the resin will be months from the shipping date.

Arkema Coating Resins 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700 **Headquarter: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

