

TECHNICAL DATA SHEET

SYNOLAC® 1035 X 60

Short Oil Alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 1035 X 60 is a short oil alkyd resin based on tall oil.
SYNOLAC® 1035 X 60 is recommended for general purpose stoving enamels, with good mechanical properties and acid catalysed lacquers

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	59 - 61 %	ISO 3251
Viscosity (Brookfield SC4-25/13R, 6.6s-1) (25°C)	6000 - 15000 mPa.s	ISO 3219
Color	7 max Gardner	ISO 4630
Acid value	15 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Flash point	25 °C	ISO 3679
Density	1.0 g/ml	ISO 2811
Fatty acid type	Tall oil fatty acid	-
Fatty acid content	38 %	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
- General Industry

PERFORMANCE BENEFITS

- Excellent gloss
- Good balance of mechanical properties
- Excellent yellowing resistance
- Excellent pigment wetting

SYNOLAC® 1035 X 60

FORMULATION GUIDELINES

SOLUBILITY

SYNOLAC® 1035 X 60 is soluble in aromatic hydrocarbons, esters, ketones, glycol ethers, partially soluble in terpenic solvents and alcohols and insoluble in aliphatic hydrocarbons.

COMPATIBILITY

SYNOLAC® 1035 X 60 is compatible with short alkyd drying resins, oil free resins, urea/formaldehyde resins, benzoguanamine resins and nitrocellulose resins. It is partially compatible with short alkyd non drying resins and melamine/formaldehyde resins and incompatible with cardura resins.

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 1035 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA