

# TECHNICAL DATA SHEET

# SYNOLAC® 140 X 60

Short Oil Alkyd

### **PRODUCT APPLICATION DETAILS**

 ${\sf SYNOLAC}^{\circ}$  140 X 60 is a short alkyd resin based on soya oil with good reactivity, suitable for short curing oven time.

 $SYNOLAC^{\circ}$  140 X 60 is recommended for general use in oven curing enamels and varnishes, nitrocellulose and acid curing lacquers.

### **SALES SPECIFICATIONS**

	CHARACTERISTICS	METHODS
Solid content (125°C)	59 - 61 %	ISO 3251
Viscosity (Brookfield SC4-25/13R, 6.6s-1) (25°C)	3100 - 4800 mPa.s	ISO 3219
Color	6 max Gardner	ISO 4630
Acid value	10 - 15 mg KOH/g	ISO 2114

## OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Flash point	27 °C	ISO 3679
Density	1.10 g/ml	ISO 2811
Fatty acid type	Soya	-
Fatty acid content	41 %	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### **MARKETS**

# **Coatings & Inks**

- Industrial Coating
  - General Industry



# SYNOLAC® 140 X 60

## **FORMULATION GUIDELINES**

### SOLUBILITY

SYNOLAC® 140 X 60 is soluble in aromatic hydrocarbons, esters, ketones and glycol ethers. It has a limited solubility in alcohols and it is insoluble in aliphatic hydrocarbons.

### **COMPATIBILITY**

SYNOLAC® 140 X 60 is compatible with many others short oil drying and non-drying alkyds, OFPE, urea and melamine formaldehyde resins, benzoguanamine and nitrocellulose. It is incompatible with medium and long oil alkyds.

### **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

### **STORAGE AND HANDLING**

SYNOLAC® 140 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided. In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

**Headquarter: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

