

## TECHNICAL DATA SHEET

# SYNOLAC® 5001-70

*Short Oil Alkyd*

### PRODUCT APPLICATION DETAILS

SYNOLAC® 5001-70 is a short oil non-oxidising alkyd resin. This resin is recommended to use with amino resins for stoving enamels and plasticizing alkyd in NC lacquers.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (at 150°C, 1gm, 1hr)	68 - 72 %	ISO 3251
Viscosity (50% Xylene, Ford Cup B-4) (at 30°C)	5 - 8 P	
Color	5 max Gardner	ISO 4630
Acid value	15 max mg KOH/g	ISO 2114

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Volatile	Xylene	
Density (at 20°C)	1.08 g/ml	ISO 2811
Fatty acid type	Coconut	
Fatty acid content	32 %	

Acid value and/or Hydroxyl value quoted relative to solid resin

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Industrial Coating
  - General Industry
  - Wood Furniture

### PERFORMANCE BENEFITS

- Excellent gloss retention
- Excellent color retention
- Excellent hardness along with adequate flexibility

# SYNOLAC® 5001-70

## FORMULATION GUIDELINES

### RECOMMENDATIONS FOR USE

SYNOLAC® 5001-70 is compatible with amino resins and is typically used in combination with Melamine formaldehyde. For an optimum performance with respect to level of cure, flexibility, hardness and impact resistance, a combination of SYNOLAC® 5001-70 with amino resin at a suitable ratio on solid resin is recommended.

### SOLUBILITY:

SYNOLAC® 5001-70 is soluble in aromatic hydrocarbons, ketones and esters.

### COMPATIBILITY:

SYNOLAC® 5001-70 is compatible with most short oil alkyds, amino resins and nitrocellulose resins.

### USES:

SYNOLAC® 5001-70 is used in stoving enamels with excellent colour retention. It is also used in NC lacquers and roller coating varnishes.

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOLAC® 5001-70 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided. In the above mentioned storage conditions the shelf life of the resin will be from the date of manufacturing.

Shelf Life (Months): 12

**Arkema Chemical India Private Ltd.**  
D-43, Trans Thane Creek MIDC  
Industrial Area 400706, Mumbai – India  
T +91 22 67377122

**Headquarter: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790