

TECHNICAL DATA SHEET

SYNOLAC® 5404 X 60

Short Oil Alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 5404 X 60 is an alkyd resin based on linoleic rich oil, designed to formulation air drying paints and general purpose stoving enamels.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	58.5 - 61.5 %	ISO 3251
Viscosity (Brookfield) (25°C)	6000 - 8500 mPa.s	ISO 3219
Color	6 max Gardner	ISO 4630
Acid value	12 - 18 mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Density	1.03 g/ml	ISO 2811
Fatty acid type	TOFA	-
Fatty acid content	30 %	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
- General Industry

PERFORMANCE BENEFITS

- Good outdoor durability
- Fast drying
- Quick hardness evolution

SYNOLAC® 5404 X 60

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOLAC® 5404 X 60 could be used in paint air drying formulation and forced drying (60°C - 80°C) using driers. SYNOLAC® 5404 X 60 combined with melamine resins allows the formulation of stoving enamels.

SOLUBILITY

SYNOLAC® 5404 X 60 is soluble in aromatic hydrocarbons (toluene xylene, aromatic solvent boiling range 155°C - 181°C, butyl acetate, PMA, diacetone, alcohols and glycol ethers).

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 5404 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

ARKEMA