

TECHNICAL DATA SHEET

SYNOLAC® 7210 X 60

Short Oil Alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 7210 X 60 is a low viscosity short oil alkyd resin based on dehydrated castor oil specially designed to be used in combination with amino resins for general purpose primers and enamels.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	58 - 62 %	ISO 3251
Viscosity (Brookfield SC4-25/13R, 6.6s-1) (25°C)	2700 - 6000 mPa.s	ISO 3219
Color	6 max Gardner	ISO 4630
Acid value	17 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene	-
Flash point	24 °C	ISO 3679
Density	1.03 g/ml	ISO 2811
Fatty acid type	Dehydrated castor oil	-
Fatty acid content	40 %	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry

PERFORMANCE BENEFITS

- High gloss
- Flexibility
- Mar resistance
- Good colour retention

SYNOLAC® 7210 X 60

FORMULATION GUIDELINES

SOLUBILITY

SYNOLAC® 7210 X 60 is soluble in aromatic hydrocarbons, esters, ketones and glycol ethers.

COMPATIBILITY

SYNOLAC® 7210 X 60 is compatible with amino resins, short and medium oil alkyd resins, nitrocellulose and alkyd resins modified with styrene. It is partially compatible with long oil alkyd resins and drying oils.

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 7210 X 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790