

TECHNICAL DATA SHEET

SYNOLAC® 7500

Very long oil alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC $^{\circ}$ 7500 is a long oil length, high solid, oxidising alkyd. SYNOLAC $^{\circ}$ 7500 exhibits good penetration into wooden substrates and very smooth wiping feel. It has very good gloss and flexibility.

SALES SPECIFICATIONS

CHARACTERISTICS	METHODS
Min. 98	ISO 3251
X-7	Gardner-Holdt
Max 8	ASTM D-1544
	ISO 2114
	Min. 98

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Nil	-
Density (25°C, g/mL)	0.99	-
Fatty acid type	Linseed Oil	-
Fatty acid content (%)	75	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Primers
 - Stains
- Industrial Coating
 - Wood Furniture
 - Wood Stains

PERFORMANCE BENEFITS

- Good flexibility
- Excellent and easy wiping
- Excellent penetration into wood
- Excellent pigment wetting
- High pigment loading



SYNOLAC® 7500

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

As a sole binder, or in combination with suitable thixotropic alkyd resins, SYNOLAC® 7500 produces paints and stains with high solids content. It is most suitable for high solid wood primers.

For decorative paints, a mixture of Cobalt and Zirconium driers to give 0.05% Cobalt and 0.15% Zirconium expressed as metals on solid resin are recommended. Where drier absorption on pigment surfaces is a potential problem or in industrially polluted atmospheres, Calcium drier up to a maximum of 0.2% metal on solid resin can be used in addition. It is normal practice to add anti-skinning agent, and methyl ethyl ketoxime at 0.1% of the total paint is recommended.

Aromatic hydrocarbon — Complete Aliphatic Hydrocarbon — Complete Alcohol — Partial

COMPATIBILITY

Long Oil Alkyd — Very Good Linseed Oil — Very Good Stand Oil — Very Good Medium Oil Alkyd — Partial Thixotropic Alkyd Resins — Good

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 7500 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 35°C. Exposure to direct sunlight should be avoided. In the above mentioned storage conditions the shelf life of the resin will be 12 months.

> Arkema Coating Resins Malaysia PLO 491, Jalan Keluli, Pasir Gudang Industrial Estate, 81700 Pasir Gudang, Johor - Malaysia T +60 7 253 6688

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex - France T +33 (0)1 49 00 80 80

