

TECHNICAL DATA SHEET

SYNOLAC® 8037 S 75 (Formely CHEMPOL® 809-2837)

PRODUCT APPLICATION DETAILS

SYNOLAC® 8037 S 75 is a high solids chain-stopped TOFA short oil alkyd, with fast tack free times and good exterior durability and toughness, for use in agricultural and heavy-duty equipment coatings.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	75 %	-
Viscosity	Z2-Z4 Gardner Holdt	-
Reduced viscosity (60% in Butyl Acetate)	F-I	-
Color	12 Gardner	-
Acid value	12 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Butyl acetate	-
Density	8.9 lbs/gal	-
Hydroxyl content	2.6 %	-
Hydroxyl number	87	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- · Industrial Coating

 - Automotive OEMAutomotive Refinish
 - General Industry

PERFORMANCE BENEFITS

- Fast Tack Free Time
- Good Exterior Durability
- Good Toughness



FORMULATION GUIDELINES

RECOMMENDATIONS OF USE

Useful in Agricultural and Heavy-Duty Equipment Coatings Auto Refinish

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8037 S 75 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

> **Arkema Coating Resins** 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

Headquarters: Arkema France 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80 Coating Resins - 2025-11-17 - Page: 2 / 2