

# TECHNICAL DATA SHEET

# SYNOLAC® 8273 S 65 (Formely CHEMPOL® 812-0173)

Modified alkyd

#### **PRODUCT APPLICATION DETAILS**

 ${\rm SYNOLAC}^{\circ}$  8273 S 65 is a rosin-modified linseed oil alkyd resin with fast tack-free and dry-through times, and excellent adhesion, gasoline resistance, and humidity resistance, for use in primers and auto OEM coatings.

## **SALES SPECIFICATIONS**

	CHARACTERISTICS	METHODS
Solid content	65 %	-
Viscosity	X-Z Gardner Holdt	-
Reduced viscosity (50% in n-Butyl Acetate)	E-G	-
Color	17 Gardner	-
Acid value	10 mg KOH/g	-

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	n-Butyl acetate/Xylene 93/7	-
Density	8.8 lbs/gal	-

<sup>&#</sup>x27;The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

#### **MARKETS**

## **Coatings & Inks**

- · Industrial Coating
  - Automotive OEM
  - General Industry

## **PERFORMANCE BENEFITS**

- Fast Free Times and Through Dry
- Excellent Gasoline Resistance
- **Excellent Adhesion**
- **Outstanding Humidity** Resistance
- Meets Federal Specifications TT-P-644 and TT-E-515



## **FORMULATION GUIDELINES**

#### **RECOMMENDATIONS OF USE**

**Primer Coatings** Auto OEM Under-hood Parts General Industrial Coatings

## **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

#### **STORAGE AND HANDLING**

SYNOLAC® 8273 S 65 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

**Arkema Coating Resins** 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

**Headquarters: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

Coating Resins - 2025-11-11 - Page: 2 / 2