

## TECHNICAL DATA SHEET

# SYNOLAC® 8298 WD 60

*Solventborne Alkyd*

### PRODUCT APPLICATION DETAILS

SYNOLAC® 8298 WD 60 is a phenolic modified chinawood oil. SYNOLAC® 8298 WD60 is supplied in low aromatic white spirit to enable the formulation of coatings that do not require adverse environmental labelling. SYNOLAC® 8298 WD60 can be formulated into a range of decorative and marine paints.

### SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (125°C)	59 - 61 %	ISO 3251
Viscosity (Brookfield LVDV-II+, SC4-34, 20rpm) (23°C)	330 - 410 mPa.s	ISO 3219
Color	9 max Gardner	ISO 4630

### OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	Low aromatic white spirit	
Flash point	40 °C	ISO 3679
Density (25°C)	0.9 g/ml	ISO 2811
Fatty acid type	Tung	
Fatty acid content	75 %	
Modification	Phenolic	

<sup>1</sup>The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

### MARKETS

#### Coatings & Inks

- Architectural Coating
  - Primers
  - Stains

### PERFORMANCE BENEFITS

- High gloss
- Good drying
- Good water resistance

# SYNOLAC® 8298 WD 60

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOLAC® 8298 WD 60 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.

In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Shelf Life Durability (Months): 6

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790