

TECHNICAL DATA SHEET

SYNOLAC® 8328 S 75 (Formely CHEMPOL® 813-1428)

Modified alkyd

PRODUCT APPLICATION DETAILS

 ${\tt SYNOLAC^{\circ}~8328~S~75~is~a~high~solids~styrene-modified~soya/DCO~oil~alkyd~with~fast~air-dry}$ times, for use in a broad range of industrial coatings.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	75 %	-
Viscosity	Z4-Z6 Gardner Holdt	-
Reduced viscosity (50% in Xylene)	F-H	-
Color	9 Gardner	-
Acid value	8 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene/MPK	-
Density	8.4 lbs/gal	-
Hydroxyl content	1.2 %	-
Hydroxyl equivalent weight	1400	-
Hydroxyl number	40	-

^{&#}x27;The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- · Industrial Coating

 - Automotive OEMAutomotive Refinish
 - General Industry



PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8328 S 75 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

> **Arkema Coating Resins** 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

Headquarters: Arkema France 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80 Coating Resins - 2025-11-11 - Page: 2 / 2