

# TECHNICAL DATA SHEET

# SYNOLAC® 8335 S 75 (Formely CHEMPOL® 813-1435)

Modified alkyd

# **PRODUCT APPLICATION DETAILS**

 ${\tt SYNOLAC^{\circ}~8335~S~75~is~a~high~solids~styrene-modified~soya/DCO~oil~alkyd~with~fast~tack-free}$ and dry-through times, for use in a broad range of industrial coatings.

# **SALES SPECIFICATIONS**

	CHARACTERISTICS	METHODS
Solid content	75 %	-
Viscosity	Z3-Z5 Gardner Holdt	-
Reduced viscosity (60% in n-Butyl Acetate)	N-R	-
Color	8 Gardner	-
Acid value	8 mg KOH/g	-

# OTHER CHARACTERISTICS<sup>1</sup>

	CHARACTERISTICS	METHODS
Solvent	n-Butyl acetate/MAK	-
Density	8.4 lbs/gal	-
Hydroxyl content	1.2 %	-
Hydroxyl equivalent weight	1400	-
Hydroxyl number	40	-

<sup>&#</sup>x27;The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

# **MARKETS**

#### **Coatings & Inks**

- · Industrial Coating

  - Automotive OEMAutomotive Refinish
  - General Industry

# **PERFORMANCE BENEFITS**

- · Fast tack free time
- · Fast through dry



# **FORMULATION GUIDELINES**

#### **RECOMMENDATIONS OF USE**

Very good exterior durability

### **PRODUCT SAFETY**

Please refer to the corresponding Safety Data Sheet.

# **STORAGE AND HANDLING**

SYNOLAC® 8335 S 75 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

> **Arkema Coating Resins** 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

**Headquarters: Arkema France** 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80 Coating Resins - 2025-11-11 - Page: 2 / 2