

TECHNICAL DATA SHEET

SYNOLAC® 8626 S 70 (Formerly CHEMPOL® 801-2426)

Long oil alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 8626 S 70 is a 70% solids air-dry soya alkyd for interior and exterior primers, paints and stains with good gloss retention, color retention, and ease of brushing.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	70 %	-
Viscosity	Z1-Z3 Gardner Holdt	-
Reduced viscosity (50% in Mineral Spirits)	D-F Gardner Holdt	-
Color	8 Gardner	-
Acid value	6 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Mineral spirits (92%)/A100 (8%)	-
Density	7.9 lbs/gal	-
Hydroxyl content	1.5 %	-
Hydroxyl number	50	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - General Industry
 - Wood Furniture

SYNOLAC® 8626 S 70

(Formerly CHEMPOL® 801-2426)

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8626 S 70 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

Arkema Coating Resins
410 Gregson Dr.
Cary, NC 27511 – USA
T +1 919 469 6700

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790