

TECHNICAL DATA SHEET

SYNOLAC® 8661 S 70 (Formely CHEMPOL® 801-7961)

Solventborne Alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 8661 S 70 is a high solids long oil alkyd for exterior porch and deck stains.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	70 %	-
Viscosity	Z1-Z3 Gardner Holdt	-
Color	7 Gardner	-
Acid value	10 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Xylene/A100/Mineral spirits (4.5/28.2/67.3)	-
Density	8.05 +/- 0.1 lbs/gal	-

^{&#}x27;The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- · Architectural Coating
 - Exterior Wall
 - Primers
 - Specialty Coatings
 - Stains
 - Trim
- Flooring
 - Floor Polish & Floor Coatings



PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8661 S 70 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

> **Arkema Coating Resins** 410 Gregson Dr. Cary, NC 27511 – USA T +1 919 469 6700

Headquarters: Arkema France 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

ARKEMA