

TECHNICAL DATA SHEET

SYNOLAC® 8666 (Formerly CHEMPOL® 801-0066)

Solventborne Alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 8666 is solvent-free soya-based long oil alkyd resin designed for use as an adhesion modifier for exterior acrylic paints and as a solids and viscosity modifier for high solids alkyd paints.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	99+ %	-
Viscosity	Z1-Z3 Gardner Holdt	-
Color	7 Gardner	-
Acid value	10 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Density	8,5 lbs/gal	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Architectural Coating
 - Exterior Wall
 - Specialty Coatings
 - Stains
 - Trim
- Flooring
 - Floor Polish & Floor Coatings

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 8666 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.