

TECHNICAL DATA SHEET

SYNOLAC® 93X-70

Short Oil Alkyd

PRODUCT APPLICATION DETAILS

SYNOLAC® 93X-70 is a short oil oxidising alkyd developed for use in a wide range of industrial; vehicle refinishing, fast air-drying and stoving applications.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (at 150°C, 1gm, 1hr)	68 - 72 %	ISO 3251
Viscosity (40% Xylene, Ford Cup B-4) (at 30°C)	60 - 70 s	
Color	8 max Gardner	ISO 4630
Acid value	15 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Volatile	Xylene	
Density (at 20°C)	1.06 g/ml	ISO 2811
Fatty acid type	Linoleic	
Fatty acid content	23 %	

Acid value and/or Hydroxyl value quoted relative to solid resin

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Packaging Coating Metal (Can And Others)

PERFORMANCE BENEFITS

- Rapid drying
- Excellent color retention
- Good hardness
- Good adhesion on metal substrates

SYNOLAC® 93X-70

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

COMPATIBILITY:

SYNOLAC® 93X-70 is partially compatible with some short and medium oil alkyd resins, amino resins. It is incompatible with long oil alkyds, chlorinated rubber, nitrocellulose and vinyl resins.

SOLUBILITY:

SYNOLAC® 93X-70 is completely soluble in aromatic hydrocarbons, ketones and esters. It does have very limited solubility in alcohols. It is not soluble in aliphatic hydrocarbons.

DRIERS:

In air drying systems 0.05%CO, 0.5%Pb, 0.1%Ca calculated as metal on solid resins content are recommended.

S.D. - 15 - 20 Min.

T.D. - 60 - 75 Min.

H.D. - O/N

In low bake system recommended temperature is 80 - 90°C and level of Melamine formaldehyde is 5-15% on solid resin.

USES:

SYNOLAC® 93X-70 is use for vehicle refinishes, fast drying Industrial finishes and heavy-duty primers.

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 93X-70 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided. In the above mentioned storage conditions the shelf life of the resin will be from the date of manufacturing.

Shelf Life (Months): 12

Arkema Chemical India Private Ltd.
D-43, Trans Thane Creek MIDC
Industrial Area 400706, Mumbai – India
T +91 22 67377122

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA