

TECHNICAL DATA SHEET

SYNOLAC® 9666 S 70

Oil free polyester

PRODUCT APPLICATION DETAILS

 ${\sf SYNOLAC}^{\tiny{\textcircled{\tiny{0}}}}$ 9666 S 70 is a saturated polyester recommended used in the coil coating industry for cost effective backers and exterior topcoats.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS	
Solid content (150°C)	69 - 71 %	ISO 3251	
Viscosity (25°C)	2500 - 3000 mPa.s	ISO 3219	
Color	4 max Gardner	ISO 4630	
Acid value	10 max mg KOH/g	ISO 2114	

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Aromatic solvent (boiling range 155°C - 181°C) / butyl glycol	-
Flash point	41 °C	ISO 3679
Density	1.08 g/ml	ISO 2811
Hydroxyl equivalent weight	50	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Coil

PERFORMANCE BENEFITS

- Capability of curing at high line speeds
- Good flexibility
- Good gloss
- Good flow
- High Yield



SYNOLAC® 9666 5 70

FORMULATION GUIDELINES

RECOMMENDATIONS FOR USE

SYNOLAC® 9666 S 70 based coatings should be modified with hexamethoxymethylmelamine (HMMM) at a resin solids ratio of between 80:20 and 90:10 polyester:amino resin. A typical curing schedule is 30-60 seconds at 230-240°C peak metal temperature.

The temperature and times will vary according to the type and gauge of the metal substrate being used.

The addition of a catalyst such as Nacure® 3525 (1) at 0.1-0.2% can assist in increasing cure rate.

Notes: (1) King Industries

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 9666 S 70 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided. In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarter: Arkema France 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

