

TECHNICAL DATA SHEET

SYNOLAC® 9675 S 65

Oil free polyester

PRODUCT APPLICATION DETAILS

SYNOLAC® 9675 S 65 is specially designed for use in exterior can coating primer with excellent adhesion and flexibility on various substrates.

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content (150°C)	64 - 66 %	ISO 3251
Viscosity (Brookfield SC4-21/13R, 19s-1) (25°C)	3000 - 4000 mPa.s	ISO 3219
Color	4 max Gardner	ISO 4630
Acid value	4 max mg KOH/g	ISO 2114

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Aromatic solvent (boiling range 155°C - 181°C) butyl glycol (68 : 32)	-
Flash point	41 °C	ISO 3679
Density	1.08 g/ml	-
Hydroxyl equivalent weight	20	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

Coatings & Inks

- Industrial Coating
 - Packaging Coating Metal (Can And Others)

PERFORMANCE BENEFITS

- High coverage performances
- Good adhesion
- Excellent flexibility
- Deep drawing properties
- Good performance in low bake cure

SYNOLAC® 9675 S 65

PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

STORAGE AND HANDLING

SYNOLAC® 9675 S 65 should be stored indoors in the original, unopened and undamaged container, in a dry place at a temperature not exceeding 30°C. Exposure to direct sunlight should be avoided.
In the above mentioned storage conditions the shelf life of the resin will be from the shipping date.

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790