

TECHNICAL DATA SHEET

SYNOLAC® 9704 ND 85 (Formerly CHEMPOL® 211-5104)

Oil free polyester

PRODUCT APPLICATION DETAILS

Low VOC  
Good Flexibility

SALES SPECIFICATIONS

	CHARACTERISTICS	METHODS
Solid content	85 %	-
Viscosity	Z4-Z6 Gardner Holdt	-
Color	4 Gardner	-
Acid value	7 mg KOH/g	-

OTHER CHARACTERISTICS¹

	CHARACTERISTICS	METHODS
Solvent	Aromatic 100	-
Density	8.8 lbs/gal	-
Hydroxyl content	4.7 %	-
Hydroxyl number	155	-

¹The data provided for these properties are typical values, intended only as guides, and should not be construed as sales specifications

MARKETS

- Coatings & Inks
- Industrial Coating
    - Coil

# SYNOLAC® 9704 ND 85

(Formerly CHEMPOL® 211-5104)

## FORMULATION GUIDELINES

### RECOMMENDATIONS OF USE

Coil polyester for appliances

## PRODUCT SAFETY

Please refer to the corresponding Safety Data Sheet.

## STORAGE AND HANDLING

SYNOLAC® 9704 ND 85 - Packaged products should be stored in a dry indoor location. The material should be stored in the original, unopened and undamaged container at storage temperatures not exceeding 85° F (30° C). Exposure to direct sunlight should be avoided. For assistance with the best practices for bulk shipment storage and handling contact Arkema.

**Arkema Coating Resins**  
410 Gregson Dr.  
Cary, NC 27511 – USA  
T +1 919 469 6700

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

